


## PLASADD® PE9172



PLASADD® PE9172 is a polyethylene based masterbatch containing a blend of a slow migration slip agent and a mildly abrasive fine natural silica. It is designed for use in the manufacture of blown polyethylene film where the end product requires slip and antiblock characteristics. The slip additive migrates to the film surface relatively slowly, thus reducing potential problems during sealing and printing.

This product is suitable for use in a wide range of plastics that come into contact with food . For more details regarding the food contact compliance in various European countries, please refer to the relevant Food Contact Statement that you can obtain through your usual Cabot representative.

**METHOD OF ADDITION**  
PLASADD® PE9172 is designed for ease of dilution and homogeneous mixing and is therefore suitable for direct addition using automatic dosing units or by pre-blending.

**ADDITION RATE**  
The addition level of the masterbatch depends on the thickness of the product, the extrusion conditions and the final application and should be tested for each new application. Typical addition levels vary from 1% to 3%.



PLASADD® PE9172

SLIP AND ANTIBLOCK  
MASTERBATCH



### PHYSICAL PROPERTIES

PROPERTY	VALUE	TEST METHOD (*)
Carrier	LDPE	
Additives	5 % erucamide 10 % natural silica	
Colour	pellets have a slight white appearance	
Compatibility	LDPE, LLDPE, HDPE, PP, EVA and other ethylene copolymers	
Density @ 23°C	980 kg/m3	CTM E023
MFI 2.16kg/190°C	10 g/10 min	CTM E005 (ISO 1133)

(\*) Tests are performed according to Cabot Test Methods (CTM) based on international Standards

Quoted test results should not be used for specification purposes but are typical test values intended for guidance only.

### PACKAGING

PLASADD® PE9172 is supplied in regular pellet form packed in 25 kg bags. It should be stored in a cool, dry place.

Recommended storage life: up to 3 months provided it is stored as directed.

This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and CABOT DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AS TO (i) SUCH INFORMATION, (ii) ANY PRODUCT OR (iii) INTELLECTUAL PROPERTY INFRINGEMENT. In no event is Cabot responsible for, and Cabot does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.

<b>HEAD OFFICE</b> Cabot SCCC Interleuvenlaan 15 I B - 3001 Leuven - Belgium Tel : +32 16 39 24 00 Fax : +32 16 39 24 44	<b>Cabot Plastics Belgium S.A.</b> Rue Prevochamps 78 B - 4860 Pepinster - Belgium Tel: +32 87 39 27 11 Fax: +32 87 46 98 69	<b>Cabot Plastics Deutschland</b> Tel: (0800) 182 40 86 Fax: (0800) 182 40 87 c/o Cabot Plastics Belgium S.A. (see address above)	<b>Cabot Plastics Hong Kong Ltd</b> 18 Dai Kwai Street Tai Po Industrial Estate / NT Hong Kong SAR - PRC Tel: +852 2666 2666 Fax: +852 2666 0807
<b>SALES OFFICES</b> Cabot Plastics Ltd Gate Street Dukinfield SK16 4RU - England Tel: +44 161 934 4500 Fax: +44 161 934 4501	<b>Cabot Latin America Division</b> Rua do Paraíso, 148 – 5th floor Paraíso CEP 04103-000 São Paulo SP - Brazil Tel: +55 11 21 44 64 00 Fax: +55 11 32 53 00 51 Tel.: (0800) 195 959 (Customer Service)	<b>Cabot Italiana S.p.A</b> Zona Industriale, 4 I - 38055 Grigno (TN) - Italia Tel: +39 0461 775 211 Fax: +39 0461 765 146	<b>Cabot (China) Limited</b> 558 Shuangbai Road Shanghai, China 201108 Tel: +86 21 5175 8800 Fax: +86 21 6434 5532

PLASBLAK®, PLASWITE®, PLASGREY®, PLASADD®, CABELECC® and CABOT® are trademarks of Cabot Corporation  
© Cabot Corporation, MA, U.S.A. All rights reserved. 2007